Version: V03.40

Oklahoma Department of Transportation Mix Design Report

Asphalt Concrete, Type S3 (PG 70-28 OK) Mat'l. Code: asco008
(Material Full Name and Material Code)

Binder ID: B1
(Design Type and Design Type ID)

Overland Corp P/S # m00433
(Producer/Supplier Name and Producer/Supplier Code)

S3pv0261600900
(Mix ID)

Overland Corp (Duncan) PLANT ID # m00433-04
(Plant Name and Plant ID)

Aggregate	Producer/Supplier	% USED
1" Rock	Hanson Aggregates, WRP Inc (Davis, OK) P/S # m001985008	27
3/8" Chips	Dolese Co (Davis, OK) P/S # m002745002	30
3/16" Scrns.	Hanson Aggregates, WRP Inc (Davis, OK) P/S # m001985008	15
Man. Sand	Martin-Marietta (Davis, OK) P/S # m002285005	13
Sand	E & A Materials (Temple, OK) P/S # m001831701	15

Asphalt Cement: Asphaltic Cement Type PG 70-28 OK, acem002, Valero (Ardmore, OK), m00352
(Material Full Name, Material Code, Producer/Supplier Name, Producer/Supplier Code)

Requires Form 93-E0 signed by the Department for production use.
-Oklahoma D.O.T. Materials-

Producer/Supplier:	Hanson Aggregates, WRP Inc (Davis, OK) P/S # m001985008	Dolese Co (Davis, OK) P/S # m002745002	Hanson Aggregates, WRP Inc (Davis, OK) P/S # m001985008	Martin-Marietta (Davis, OK) P/S # m002285005	E & A Materials (Temple, OK) P/S # m001831701								
Sieve Size	1" Rock	3/8" Chips	3/16" Scrns.	Man. Sand	Sand				Comb. Agg.	JMF	Min.	Max.	% Tol. (±)
1 in (25 mm)	100	100	100	100	100				100	100	100	100	0
3/4 in (19 mm)	69	100	100	100	100				92	92	85	99	7
1/2 in (12.5 mm)	19	100	100	100	100				78	78	71	85	7
3/8 in (9.5 mm)	5	97	100	100	100				73	73	66	80	7
#4 (4.75 mm)	1	22	100	94	100				49	49	42	56	7
#8 (2.36 mm)	1	3	72	54	100				34	34	29	39	5
#16 (1.18 mm)	1	2	47	30	100				27	27	23	31	4
#30 (.600 mm)	1	1	32	18	96				22	22	18	26	4
#50 (.300 mm)	1	1	23	10	50				13	13	9	17	4
#100 (.150 mm)	1	1	16	6	3				4	4	1	7	3
#200 (.075 mm)	1.2	1.2	11.6	3.7	1.0				3.1	3.1	1.1	5.1	2
AC Content %									4.5	4.5	4.1	4.9	0.4

	°F (°C)	Required
Mix temperature @ discharge from mixer:	325 (163)	± 20 °F (± 10 °C)
Optimum roadway compaction temperature:	305 (152)	
Laboratory mixing temperature:	325 (163)	
Laboratory compaction temperature:	300 (149)	

Tests on Asphalt Cement	Found
Specific Gravity @ 77 ° F	1.0100

Requires Form 93-E0 signed by the Department for production use.
-Oklahoma D.O.T. Materials-

Tests on Compressed Mixtures (@ Design AC)	# Gyr.	% Density of Gmm	% Density Required
Nini	7	89.2	85.5 - 90.5
Ndes	65		96.0

Tests on Aggregates		Required		Units
Durability Index	71	40	min.	%
F.A.A. %U		N/A		%
Flat and Elongated	0	10	max.	%
Fractured Faces	100/100	95/90	min.	%
Insoluble Residue	47.9	N/A		%
LA Abrasion	28	40	max.	%
Micro-Deval	13.9	N/A		%
Permeability	9	12.5	max.	10^{-5}cm/s
Sand Equivalent	82	45	min.	%
IOC	0.48			%
Gse	2.675			
Gsb	2.653			
Specimen Weight	4860			g

Tests on Compressed Mixtures

%AC	Gmb	Gmm	% Density of Gmm	% Density Required	% VMA	% VMA Required	% VFA	% VFA Required
4.3	2.383	2.498	95.4	Design / Field	14.0	Design / Field	67.1	
4.8	2.406	2.479	97.1	96.0 / 94.5 - 97.4	13.7	13.5 / 13.0	78.8	70 - 75
5.3	2.424	2.460	98.5		13.5		88.9	

Dust Prop.	Dust Prop. Req.
0.8	0.6 - 1.6
0.7	
0.6	

ITS (PSI) 112.2 N/A min.
TSR 0.81 0.80 / 0.75 min. (Design / Field)
Compacted Wt. (lbs/sy/1" thick) = 109.6 @ 4.5 % Asphalt Cement

Hamburg Rut Test Depth (mm) 3.35 12.50 max. @ 15,000 cycles

MEETS SPECIFICATION REQUIREMENTS PER SPECIAL PROVISION 708-26(a-f) 09

Comments:

Last Modified By: Williams, Bobby Ray bwilli01
(User Name and User ID)

Date: 1/4/2017
(mm/dd/yyyy)