Version: V03.40

Oklahoma Department of Transportation Mix Design Report

Asphalt Concrete, Type S4 (PG 64-22 OK) Mat'l. Code: asco012
(Material Full Name and Material Code)

Binder - Recycled ID: B2
(Design Type and Design Type ID)

Haskell Lemon Const Co (Asphalt) P/S # m00428
(Producer/Supplier Name and Producer/Supplier Code)

S4qc0381491000
(Mix ID)

Haskell Lemon (East OKC, OK) - 350TPH PLANT ID # m00428-02
(Plant Name and Plant ID)

Aggregate	Producer/Supplier	% USED
5/8" Chips	Dolese Co (Davis, OK) P/S # m002745002	28
Man. Sand	Martin-Marietta (Davis, OK) P/S # m002285005	13
C-33 Scrns.	Martin-Marietta (Snyder, OK) P/S # m002323802	24
Sand	General Materials Inc (Oklahoma City, OK) P/S # m009215515	10
Coarse R.A.P.	Contractor / Project Site P/S # Contractor	25

Asphalt Cement: Asphaltic Cement Type PG 64-22 OK, acem003, Lion Oil Co. (Muskogee, OK), m00511
(Material Full Name, Material Code, Producer/Supplier Name, Producer/Supplier Code)

Requires Form 93-E0 signed by the Department for production use.
-Oklahoma D.O.T. Materials-

Producer/Supplier:	Dolese Co (Davis, OK) P/S # m002745002	Martin-Marietta (Davis, OK) P/S # m002285005	Martin-Marietta (Snyder, OK) P/S # m002323802	General Materials Inc (Oklahoma City, OK) P/S # m009215515	Contractor / Project Site P/S # Contractor								
Sieve Size	**5/8" Chips**	**Man. Sand**	**C-33 Scrns.**	**Sand**	**Coarse R.A.P.**				**Comb. Agg.**	***JMF***	***Min.***	***Max.***	***% Tol. (±)***
3/4 in (19 mm)	100	100	100	100	100				100	***100***	*100*	*100*	*0*
1/2 in (12.5 mm)	91	100	100	100	95				96	***96***	*89*	*100*	*7*
3/8 in (9.5 mm)	60	100	100	100	86				85	***85***	*78*	*92*	*7*
#4 (4.75 mm)	5	93	94	99	52				59	***59***	*52*	*66*	*7*
#8 (2.36 mm)	3	55	71	99	37				44	***44***	*39*	*49*	*5*
#16 (1.18 mm)	3	27	48	97	29				33	***33***	*29*	*37*	*4*
#30 (.600 mm)	2	14	28	90	24				24	***24***	*20*	*28*	*4*
#50 (.300 mm)	2	7	13	65	18				16	***16***	*12*	*20*	*4*
#100 (.150 mm)	1	4	5	16	11				6	***6***	*3*	*9*	*3*
#200 (.075 mm)	1.0	3.3	3.1	1.5	6.2				3.2	***3.2***	*1.2*	*5.2*	*2*
AC Content %					3.6				4.8	***4.8***	*4.4*	*5.2*	*0.4*

	°F (°C)	Required
Mix temperature @ discharge from mixer:	305 (152)	± 20 °F (± 10 °C)
Optimum roadway compaction temperature:	290 (143)	
Laboratory mixing temperature:	325 (163)	
Laboratory compaction temperature:	300 (149)	

Tests on Asphalt Cement	Found
Specific Gravity @ 77 °F	1.0100

Requires Form 93-E0 signed by the Department for production use.
-Oklahoma D.O.T. Materials-

Tests on Compressed Mixtures (@ Design AC)

	# Gyr.	% Density of Gmm	% Density Required
Nini	6	89.5	85.5 - 91.5
Ndes	50		96.0

Tests on Aggregates		Required		Units
Durability Index	75	40	min.	%
F.A.A. %U		N/A		%
Flat and Elongated	0	10	max.	%
Fractured Faces	100/100	85/80	min.	%
Insoluble Residue		N/A		%
LA Abrasion	27	40	max.	%
Micro-Deval	16.4	N/A		%
Permeability	7.9	12.5	max.	10^{-5}cm/s
Sand Equivalent	82	40	min.	%
IOC	0.12			%
Gse	2.674			
Gsb	2.647			
Specimen Weight	4835			g

Tests on Compressed Mixtures

%AC	Gmb	Gmm	% Density of Gmm	% Density Required Design / Field	% VMA	% VMA Required Design / Field	% VFA	% VFA Required
4.3	2.359	2.497	94.5		14.7		62.6	
4.8	2.378	2.478	96.0	96.0 / 94.5 - 97.4	14.5	14.5 / 14.0	72.4	72 - 77
5.3	2.397	2.459	97.5		14.2		82.4	

Dust Prop.	Dust Prop. Req.
0.8	
0.7	0.6 - 1.6
0.7	

ITS (PSI) 123 N/A min.
TSR 0.91 0.80 / 0.75 min. (Design / Field)
Compacted Wt. (lbs/sy/1" thick) = 109.0 @ 4.8 % Asphalt Cement
3.9 % New Asphalt Cement

Hamburg Rut Test Depth (mm) 7.48 12.50 max. @ 10,000 cycles

MEETS SPECIFICATION REQUIREMENTS PER SPECIAL PROVISION 708-26(a-f) 09

Comments:

Last Modified By: Schratwieser, Edward P. eschratw
(User Name and User ID)

Date: 9/10/2015
(mm/dd/yyyy)