



Oklahoma Department of Transportation Mix Design Report

Asphalt Concrete, Type S3 (PG 64-22 OK) Mat'l. Code: asco009
 (Material Full Name and Material Code)

Binder - Recycled ID: B2
 (Design Type and Design Type ID)

Venture Corporation P/S # m00719
 (Producer/Supplier Name and Producer/Supplier Code)

WS3qc0411800300
 (Mix ID)

Venture Corporation #5- Portable PLANT ID # m00719-01
 (Plant Name and Plant ID)

Aggregate	Producer/Supplier	% USED
3/8" Chips	Martin-Marietta (Mill Creek, OK) P/S # m002303502	20
Man. Sand	Martin-Marietta (Mill Creek, OK) P/S # m002303502	5
'C' Rock	Martin Marietta Mill Creek Limestone P/S # m005253504	35
Man. Sand	Martin Marietta Mill Creek Limestone P/S # m005253504	5
Sand (Unlisted Source)	Larry Hutchinson Sand	10
Fine R.A.P.	Contractor / Project Site P/S # Contractor	25

Warm Mix Asphalt (WMA) Technology	EVOTHERM (Chem. Add.) qual028 Ingevity m00941 (Product Name, Material Code, Producer/Supplier Name, Producer/Supplier Code)
Asphalt Additive, Anti-Strip	AD-HERE HP-PLUS addi003 ARR-MAZ Products, LP (Winter Haven, FL) m00070 (Product Name, Material Code, Producer/Supplier Name, Producer/Supplier Code)
Asphalt Cement:	Asphaltic Cement Type PG 64-22 OK, acem003, Coastal Energy (Clinton, OK), m01042 (Material Full Name, Material Code, Producer/Supplier Name, Producer/Supplier Code)

Sieve Size	Producer/Supplier:							Comb. Agg.	Requires Form 93-E0 signed by the Department for production use. -Oklahoma D.O.T. Materials-			
	Martin-Marietta (Mill Creek, OK) P/S # m002303502	Martin-Marietta (Mill Creek, OK) P/S # m002303502	Martin Marietta Mill Creek Limestone P/S # m005253504	Martin Marietta Mill Creek Limestone P/S # m005253504	Larry Hutchinson Sand	Contractor / Project Site P/S # Contractor			JMF	Min.	Max.	% Tol. (±)
1 in (25 mm)	100	100	100	100	100	100	100	100	100	100	100	0
3/4 in (19 mm)	100	100	100	100	100	100	100	100	100	93	100	7
1/2 in (12.5 mm)	100	100	71	100	100	100	98	89	89	82	96	7
3/8 in (9.5 mm)	95	100	26	100	100	95	72	72	65	79	7	7
#4 (4.75 mm)	35	99	3	100	100	70	46	46	39	53	7	7
#8 (2.36 mm)	9	82	2	84	100	49	33	33	28	38	5	5
#16 (1.18 mm)	5	56	2	62	100	36	27	27	23	31	4	4
#30 (.600 mm)	3	35	2	46	94	27	22	22	18	26	4	4
#50 (.300 mm)	3	16	2	29	54	20	14	14	10	18	4	4
#100 (.150 mm)	2	8	2	15	13	14	7	7	4	10	3	3
#200 (.075 mm)	1.5	5.1	1.1	5.4	3.7	10.1	4.1	4.1	2.1	6.1	2	2
AC Content %								4.8	4.8	4.4	5.2	0.4
Asphalt Additive, Anti-Strip %								0.5				
Warm Mix Asphalt (WMA) Additive %								0.3				

Mix temperature @ discharge from mixer: 275 (135) ± 20 °F (± 10 °C)
 Optimum roadway compaction temperature: 230 (110)
 Laboratory mixing temperature: 275 (135)
 Laboratory compaction temperature: 265 (129)

Tests on Aggregates	Required	Units
Contabro	N/A	%
Durability Index	90	40 min. %
F.A.A. %U	N/A	%
Flat and Elongated	0	10 max. %
Fractured Faces	100/100	85/80 min. %
Insoluble Residue	N/A	%
LA Abrasion	31	40 max. %
Micro-Deval	12.6	N/A %
Permeability	10.9	12.5 max. 10 ⁻⁵ cm/s
Sand Equivalent	75	40 min. %
Pba	0.28	
IOC	0.15	%
Gse	2.745	
Gsb	2.724	
Specimen Weight	4875	g

Tests on Asphalt Cement	Found
Specific Gravity @ 77 °F	1.0100

Requires Form 93-E0 signed by the Department for production use. -Oklahoma D.O.T. Materials-

	% Density		
	# Gyr.	of Gmm	% Density Required
Nini	6	88.9	85.5 - 91.5
Ndes	50		96.0

Tests on Compressed Mixtures							
%AC	Gmb	Gmm	% Density		% VMA	% VMA Required	% VFA
			of Gmm	% Density Required			
4.3	2.420	2.556	94.7	Design / Field	15.0	Design / Field	64.7
4.8	2.434	2.536	96.0	96.0 / 94.5 - 97.4	14.9	13.5 / 13.0	73.2
5.3	2.460	2.516	97.8		14.5		84.8

Dust Prop.
 1.0 Dust Prop. Req.
 0.9 0.6 - 1.6
 0.8

ITS (PSI) 105.6 N/A min.
TSR 0.83 0.80 / 0.75 min. (Design / Field)
 Compacted Wt. (lbs/sy/1" thick) = 111.6 @ 4.8 % Asphalt Cement
 3.3 % New Asphalt Cement

Hamburg Rut Test Depth (mm) 1.79 12.50 max. @ 10,000 cycles

MEETS SPECIFICATION REQUIREMENTS PER SPECIAL PROVISION 708-26(a-f) 09

Comments: _____

Last Modified By: Smith, Jerry D. jsmith Date: 7/11/2018
 (User Name and User ID) (mm/dd/yyyy)