

Oklahoma Department of Transportation

Coarse Aggregate Gradation for Portland Cement Concrete Construction Control Directive No. **19970605**

February 15, 2002


Scope: To modify the coarse aggregate gradation for Portland Cement Concrete.

The coarse aggregate gradation specification for P.C. Concrete has been adjusted to allow from 0% to 2% passing the No. 200 sieve, for gradation sizes 57, 67 and 7. Refer to Section 701.06 of the 1988 Standard Specifications. The adjustments are as follows:

701.06. COARSE AGGREGATE: Revise the requirements for the No. 200 in the table in Subsection (c) as follows:

| Sieve Size | No. 3 (2" to 1") | No. 357 (2" to #4) | No. 57 (1" to #4) | No. 67 3/4" to No. 4) | No. 7 (1/2" to #4) |
|------------|---------------------|-----------------------|----------------------|--------------------------|-----------------------|
| No. 200 | 0-1.5 | 0-1.5 | 0-2.0 | 0-2.0 | 0-2.0 |

This adjustment will apply to projects let under the 1988 Specifications. If needed, you may apply this gradation to the 1988 Specifications with a "no cost" change order.



George Raymond, P.E.
Construction Engineer