

**OKLAHOMA DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION
FOR
WARM MIX ASPHALT**

These Special provisions revise, amend and where in conflict, supersede applicable sections of the 1999 Standard Specifications for Highway Construction, English and Metric, as applicable. Units of measurement are provided in the subsections in both English and Metric equivalents. The units applicable for this project will be those specified in the project plans.

(Add the following:)

411.01 DESCRIPTION

Warm Mix Asphalt (WMA) is defined as an asphalt binder and aggregate mixture which, by additive or process, can be produced and placed at a reduced temperature from normal HMA temperatures. WMA requirements are the same as for HMA except where noted.

(Add the following:)

411.04 CONSTRUCTION METHODS

(j) Compaction

(1) General. Ensure that the WMA immediately behind the paver is at least 215°F [102°C].