

**OKLAHOMA DEPARTMENT OF TRANSPORTATION
SPECIAL PROVISION
FOR
NT TACK MATERIAL**

These Special Provisions revise, amend, and where in conflict, supersede applicable sections of the 2009 Standard Specifications for Highway Construction, English and Metric.

407.02 MATERIALS (*Add the following:*)

Provide NT tack material in accordance with Special Provision 708-25, “Material Requirements for Non-Tracking (NT) Tack Material.”

407.04 CONSTRUCTION METHODS

B. Fog Seal (*Add the following:*)

When applying NT tack material (NTQS-1HH, NTSS-1HM) as fog seal, dilute the emulsion at a rate of 5:1 water to original emulsion, and apply the mixture at a rate of 0.1 gal/yd² [0.44 L/m²]. Alter the application rate as directed by the Engineer (based on the pavement surface texture).

C. Tack Coat (*Add the following:*)

When applying NT tack material (CBC-1H, NTQS-1HH, NTSS-1HM) as tack coat, apply the emulsion at a rate of 0.08 gal/yd² [0.36 L/m²] of original emulsion, unless otherwise required by the Contract. Apply NT tack material (NTHAP) at a rate of 0.08 gal/yd² [0.36 L/m²] of residual asphalt content, unless otherwise required by the Contract. Alter the application rate based on the pavement surface texture, and as directed by the Engineer.

407.06 BASIS OF PAYMENT (*Add the following:*)

The Department will pay for each pay item at the contract unit price per the specified pay unit as follows:

Pay Item:	Pay Unit:
<i>(D) NT TACK MATERIAL</i>	Gallon [Liter]

The Department considers the cost of water for dilution to be included in the contract unit price for *NT Tack Material* emulsions.