

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Sampled / Tested Material			
Matl. Name	Matl. Cd.	Spec.	Tst. Meth.
HC Conc Aggregate, Fine	aggr054	701.05	C94037

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
APAC Central - Arkhola S & G (Van Buren, AR)	m001327901	Arkansas	7901

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9436942204201009	4/20/2022	1	2.44	106	2.617	1
Natural	9438872106291110	6/29/2021	1	3.19	113	2.748	1
Natural	9620781602251200	2/25/2016	IAS 1	2.42	109	2.608	2
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.68	109	2.658	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.68	109	2.658	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Hanson Aggregates (Wilton, AR)	m009167916	Arkansas	7916

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9800751806201110	6/20/2018	1	2.93	113	2.589	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.93	113	2.589	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
J & R Sand Co, Winchell Pit (Beaver Co., OK)	m002050402	Beaver Co.	0402

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	6230912206281430	6/28/2022	1	2.86	110	2.629	1
Natural	9838641804121130	4/12/2018	1	2.83	109	2.635	1
Natural	9420021303051425	3/5/2013	1	3.09	99	2.571	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.93	106	2.612	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.93	106	2.612	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Woodward Concrete Sand Pit (Gate, OK)	m010410404	Beaver Co.	0404

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434241410291122	10/29/2014	1	2.40	105	2.609	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.40	105	2.609	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Alan Ritchey Materials Co (ARMCO) (Yuba, OK)	m006120707	Bryan Co.	0707

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9436942108191225	8/19/2021	David	2.52	109	2.596	1
Natural	9436942108191225	8/19/2021	Kate	2.65	110	2.616	1
Natural	9440082006011240	6/1/2020	1	2.65	112	2.604	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.61	110	2.605	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.61	110	2.612	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Quality Sand & Gravel Sand Plant (Yuba, OK)	m012330708	Bryan Co.	0708

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082011041145	11/4/2020	1	2.93	108	2.608	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.93	108	2.608	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
RBQ Sand and Gravel (Hugo, OK)	m011631212	Choctaw Co.	1212

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082303141319	3/14/2023	1	2.53	110	2.602	1
Natural	9438872108191410	8/19/2021	John	2.69	109	2.608	1
Natural	9438872108191410	8/19/2021	Shawn	2.66	109	2.590	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.63	109	2.600	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.59	109	2.599	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Black Mesa Sand, LLC (Boise City, OK)	m009401301	Cimarron Co.	1301

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9426291702171400	2/17/2017	1	2.22	102	2.546	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.22	102	2.546	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Carder, Inc. (N. Lamar, CO)	m007088105	Colorado	8105

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9420021303061000	3/28/2013	1	3.02	102	2.569	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				3.02	102	2.569	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Carder, Inc. (SbarC Farms E. Lamar, CO)	m008088107	Colorado	8107

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9420021303061030	3/6/2013	1	2.85	109	2.597	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.85	109	2.597	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Prowers Aggregate West Farm Pit (Lamar, CO)	m010578112	Colorado	8112

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434241501121430	1/12/2015	1	2.99	109	2.606	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.99	109	2.606	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Vulcan Materials Waurika Sand (Waurika, OK)	m001831701	Cotton Co.	1701

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9840082209131136	9/13/2022	1	2.65	112	2.626	1
Natural	9440082207061212	7/6/2022	1	2.47	111	2.622	1
Natural	9440082006081140	6/8/2020	1	2.45	108	2.612	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.52	110	2.620	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.57	111	2.616	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Kline Sand (Camargo, OK)	m005932206	Dewey Co.	2206

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082001091015	1/9/2020	1	2.73	110	2.622	1
Natural	9625241604121020	4/12/2016	1	2.41	105	2.624	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.57	108	2.623	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Woodward Concrete Sand Pit (Laverne, OK)	m002893002	Harper Co.	3002

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9625241602021115	2/2/2016	IAS 1	2.35	103	2.599	1
Natural	9434241501131010	1/13/2015	1	2.20	107	2.617	1
Natural	9434241410291010	10/29/2014	1	2.20	107	2.617	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.25	106	2.611	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.25	106	2.611	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
T. & G. Const., Inc. (Lawton, OK)	m008713305	Jackson Co.	3305

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082005061030	5/6/2020	1	2.47	105	2.601	1
Natural	96224116022525110	2/25/2016	IAS 1	2.43	104	2.595	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.45	105	2.598	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Border Sands (Terral, OK)	m011973401	Jefferson Co.	3401

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440081912031100	12/3/2019	1	2.63	107	2.608	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	107	2.608	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Martin-Marietta Mill Creek Granite	m002303502	Johnston Co.	3502

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Blend	9440082305231343	5/23/2023	1	2.47	113	2.661	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.47	113	2.661	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Assoc Material & Supply Mulvane Sand (Mulvane, KS)	m001358010	Kansas	8010

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082108171032	8/17/2021	David C.	2.75	111	2.605	1
Natural	9440082108171032	8/17/2021	Kate U.	2.81	111	2.608	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.78	111	2.607	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Cornejo and Sons, LLC (Oxford, KS)	m001278011	Kansas	8011

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082211011118	11/1/2022	1	2.77	111	2.580	1
Natural	9440082009031145	9/3/2020	1	2.72	113	2.603	1
Natural	9440082007201120	7/20/2020	1	2.14	107	2.611	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.54	110	2.598	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	111	2.599	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Dolese - White Eagle Sand Plant (Ponca City, OK)	m012273608	Kay Co.	3608

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082308161314	8/16/2023	1	2.55	111	2.608	2
Natural	9440082009141055	9/14/2020	1	2.85	108	2.612	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.70	110	2.610	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u> Sober Sand Co. (Ponca City, OK)	<u>P/S Code</u> m005373601	<u>Geog. Area</u> Kay Co.	<u>Pit Num.</u> 3601
---	--------------------------------------	-------------------------------------	--------------------------------

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082211010944	11/1/2022	1	2.89	111	2.606	2
Natural	9840082209121150	9/12/2022	1	3.37	116	2.602	1
Natural	9440081910221315	10/22/2019	1	2.63	111	2.605	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.96	113	2.604	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.97	113	2.606	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Dolese Co (Dover, OK)	m001763702	Kingfisher Co.	3702

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082303061053	3/6/2023	1	2.54	106	2.611	1
Natural	9440082001091415	1/9/2020	1	2.76	107	2.602	1
Natural	9825241808160930	8/16/2018	1	2.58	109	2.671	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.63	107	2.628	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.55	108	2.627	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Dover Sand Plant, LLC (Kingfisher, OK)	m009303705	Kingfisher Co.	3705

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082008101045	8/10/2020	1	2.66	108	2.460	1
Natural	9440082005131135	5/13/2020	1	2.06	104	2.594	1
Natural	9625241901090935	1/9/2019	IAS 1	3.00	108	2.592	1
Number of Tests:				5	5	5	5
Last 3 Tests Avg.:				2.57	107	2.549	1
Last 5 Tests Avg.:				2.43	107	2.570	1
Last 10 Tests Avg.:							
Total Avg.:				2.43	107	2.570	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Duit Construction Company (Dover, OK)	m008513704	Kingfisher Co.	3704

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082303061113	3/6/2023	1	2.54	109	2.616	1
Natural	9440082001091430	1/9/2020	1	2.68	106	2.597	1
Natural	9825241808160900	8/16/2018	1	2.41	110	2.589	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.54	108	2.601	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.52	108	2.605	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Lightle Sand Co (Hennessey, OK)	m002253701	Kingfisher Co.	3701

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082303061149	3/6/2023	1	2.93	111	2.627	1
Natural	9440082005131055	5/13/2020	1	2.67	101	2.621	1
Natural	9625241602230915	2/23/2016	1	2.60	110	2.565	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.73	107	2.604	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.73	107	2.604	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
River Valley Arkoma Sand (Arkoma, OK)	m011194008	Le Flore Co.	4008

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9436942108171030	8/17/2021	John M.	2.50	109	2.618	1
Natural	9436942108171030	8/17/2021	Shawn A.	2.47	111	2.607	1
Natural	9827891907170936	7/17/2019	1	2.66	110	2.597	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.54	110	2.607	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.53	110	2.606	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u> Spiro Sand Co. (Spiro, OK)	<u>P/S Code</u> m005394001	<u>Geog. Area</u> Le Flore Co.	<u>Pit Num.</u> 4001
--	--------------------------------------	--	--------------------------------

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9621531607111130	7/11/2016	1	2.35	108	2.621	1
Natural	9620781602251100	2/25/2016	IAS 1	2.35	106	2.614	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.35	107	2.618	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Dolese Co. North Plant (Guthrie, OK)	m009094203	Logan Co.	4203

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082303060942	3/6/2023	1	2.73	109	2.618	1
Natural	9440082005041310	5/4/2020	1	2.60	109	2.615	2
Natural	9434281510290902	10/29/2015	1	2.59	108	2.625	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.64	109	2.619	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.55	109	2.622	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Van Eaton Ready Mix (NW of Guthrie, OK)	m005464202	Logan Co.	4202

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082201121441	1/12/2022	1	2.47	106	2.601	2
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.47	106	2.601	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Redi-Mix Concrete Sand (Thackerville, OK)	m011324302	Love Co.	4302

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9834451803271000	3/27/2018	1	2.03		2.611	1
Number of Tests:				1		1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.03		2.611	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Thackerville Sand & Gravel (Thackerville, OK)	m001974301	Love Co.	4301

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Blend	9840051901241000	1/24/2019	blended	2.77	114	2.599	1
	9840051901241000	1/24/2019	man sand	3.71	104	2.574	1
Natural	9840051901241000	1/24/2019	natural	2.00	110	2.618	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.83	109	2.597	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.83	109	2.597	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Kline Materials Cimarron Sand Plant (Waynoka, OK)	m012614704	Major Co.	4704

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082106151312	6/15/2021	1	2.76	108	2.617	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.76	108	2.617	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Rockin B Sand and Gravel LLC (Cleo Springs, OK)	m001864701	Major Co.	4701

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082001091230	1/9/2020	1	2.34	108	2.610	1
Natural	9625241602251315	2/25/2016	IAS 1	2.92	112	2.670	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	110	2.640	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Martin-Marietta (Eagletown, OK)	m001374502	McCurtain Co.	4502

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9438872106031100	6/3/2021	1	2.55	141	2.608	2
Natural	9434281509031147	9/4/2015	1	2.70	107	2.563	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	124	2.586	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
APAC Central - Arkhola Muskogee Sand Plant	m001315103	Muskogee Co.	5103

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9438872304111216	4/11/2023	1	2.98	112	2.611	1
Natural	9440082004301030	4/30/2020	1	2.68	108	2.613	1
Natural	9434281507140915	7/14/2015	1	2.59	110	2.621	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.75	110	2.615	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.75	110	2.615	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Muskogee Sand - West Plant (Muskogee, OK)	m007067309	Muskogee Co.	7309

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9438872304111246	4/11/2023	1	2.35	111	2.604	2
Natural	9440082004301010	4/30/2020	1	2.53	107	2.612	1
Natural	9434241409241241	9/24/2014	1	2.40	111	2.608	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.43	110	2.608	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.43	110	2.608	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Pryor Sand (Whitefield, OK)	m002455105	Muskogee Co.	5105

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082006051205	6/5/2020	1	2.60	108	2.616	1
Natural	9434241409241052	9/24/2014	1	2.90	111	2.632	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.75	110	2.624	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
R & M Resources (Okemah, OK)	m010325401	Okfuskee Co.	5401

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434241407150900	7/15/2014	1	2.90	106	2.617	2
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.90	106	2.617	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u> Dolese Co. (Oklahoma City, OK)	<u>P/S Code</u> m009225516	<u>Geog. Area</u> Oklahoma Co.	<u>Pit Num.</u> 5516
--	--------------------------------------	--	--------------------------------

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082005131435	5/13/2020	1	2.62	106	2.620	2
Natural	9434281512170200	12/17/2015	1	2.63	108	2.608	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	107	2.614	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Dolese Co. Jones Sand Plant (Jones, OK)	m004615517	Oklahoma Co.	5517

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082306151331	6/15/2023	1	2.67	108	2.619	1
Natural	9440082201141010	1/14/2022	1	2.54	115	2.606	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.61	112	2.613	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
General Materials Inc (Oklahoma City, OK)	m009215515	Oklahoma Co.	5515

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9625741602010945	2/1/2016	resample1	2.40	107	2.611	1
Natural	9434281512171220	12/17/2015	1	2.20	106	2.620	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.30	107	2.616	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
North Canadian Holding, Inc. (Edmond, OK)	m005415509	Oklahoma Co.	5509

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082008101345	8/10/2020	1	1.89	106	2.606	1
Natural	9440082006031130	6/3/2020	1	2.01	95	2.580	1
Natural	9625741602010900	2/1/2016	resample	2.49	104	2.618	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.13	102	2.601	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.15	101	2.602	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Panther Sand Co., LLC (Oklahoma Co., OK)	m002905508	Oklahoma Co.	5508

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9425741910231000	10/23/2019	1	2.64	112	2.621	1
Natural	9434281025160840	10/25/2016	1	2.54	111	2.590	1
Natural	9434281607110915	7/11/2016	1	1.97	104	2.597	1
Number of Tests:				5	5	5	5
Last 3 Tests Avg.:				2.38	109	2.603	1
Last 5 Tests Avg.:				2.16	108	2.603	1
Last 10 Tests Avg.:							
Total Avg.:				2.16	108	2.603	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Schwarz Sand Douglas Pit (Oklahoma City, OK)	m002535510	Oklahoma Co.	5510

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440081910220805	10/22/2019	1	2.83	108	2.576	1
Natural	9625741603140900	3/14/2016	IA 1	2.36	108	2.629	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.60	108	2.603	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Gellenbeck Sand Products (Perkins, OK)	m012186004	Payne Co.	6004

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082008311105	8/31/2020	1	2.63	108	2.604	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	108	2.604	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Engel Sand Co. (Ada, OK)	m001896201	Pontotoc Co.	6201

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9438872306291052	6/29/2023	1	2.29	106	2.579	3
Natural	9440082008181050	8/18/2020	1	2.58	105	2.568	1
Natural	9434241405211115	5/21/2014	1	2.67	104	2.531	2
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.51	105	2.559	2
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.51	105	2.559	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Enrem Materials, LLC (Prague, OK)	m007346304	Pottawatomie Co	6304

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082202160946	2/16/2022	1	2.87	105	2.621	1
Natural	9440082008270930	8/27/2020	1	2.61	106	2.608	2
Natural	9440082006030955	6/3/2020	1	2.18	98	2.601	1
Number of Tests:				5	5	5	5
Last 3 Tests Avg.:				2.55	103	2.610	1
Last 5 Tests Avg.:				2.43	103	2.616	1
Last 10 Tests Avg.:							
Total Avg.:				2.43	103	2.616	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Oklahoma Aztec Co. (Pottawatomie Co., OK)	m001366301	Pottawatomie Co	6301

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9438872306290947	6/29/2023	1	2.83	108	2.551	2
Natural	9440082102021440	2/2/2021	1	2.56	105	2.544	2
Natural	9440082005041030	5/4/2020	1	3.05	105	2.527	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.81	106	2.541	2
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.81	106	2.545	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
B&B Sand & Gravel (Seminole Co., OK)	m005426708	Seminole Co.	6708

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082202161040	2/16/2022	1	2.77	105	2.623	1
Natural	9440081910220955	10/22/2019	1	2.88	110	2.623	1
Natural	9434241408110855	8/11/2014	1	2.60	109	2.630	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.75	108	2.625	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.75	108	2.625	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Hoffman - Wilson Land, LLC (S. of Sallisaw, OK)	m008416805	Sequoyah Co.	6805

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434241409240950	9/24/2014	1	2.50	106	2.606	2
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.50	106	2.606	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u> Robinson Sand & Gravel	<u>P/S Code</u> m015064010	<u>Geog. Area</u> Sequoyah Co.	<u>Pit Num.</u> 4010
--	--------------------------------------	--	--------------------------------

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9840082212011239	12/1/2022	1	2.14	103	2.607	3
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.14	103	2.607	3

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Big Creek Sand & Gravel (Sanford, TX)	m001617806	Texas (State)	7806

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434281109161100	11/9/2016	1	2.36	106	2.605	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.36	106	2.605	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Hanson Aggregates Arena Plant (Garwood, TX)	m009787831	Texas (State)	7831

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434281610191450	10/19/2016	1	2.85	107	2.580	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.85	107	2.580	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Hanson Bristol Sand and Gravel (Ennis, TX)	m011937833	Texas (State)	7833

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9400001910110000	10/11/2019	1	2.74	106	2.655	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.74	106	2.655	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Lattimore Materials (Bells, TX)	m002227802	Texas (State)	7802

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9620781602031415	2/3/2016	1	2.70	101	2.564	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.70	101	2.564	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
LS Sand & Gravel (Vega, TX)	m007847824	Texas (State)	7824

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9838861805031128	5/3/2018	1	2.63	108	2.612	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.63	108	2.612	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Martin-Marietta Bells-Savoy Sand Plant	m012997835	Texas (State)	7835

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082210061119	10/6/2022	1	2.49	110	2.605	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.49	110	2.605	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Multisources, LTD Pit #7 (San Antonio, TX)	m001537818	Texas (State)	7818

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9420021303061300	3/6/2013	1	2.73	106	2.597	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.73	106	2.597	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Trinity Materials, Inc. (Waco, TX)	m008677827	Texas (State)	7827

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9420021303051130	3/5/2013	1	2.73	106	2.599	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.73	106	2.599	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
XIT Sand & Gravel (Channing, TX)	m008077825	Texas (State)	7825

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9838861805031310	5/3/2018	1	2.77	110	2.610	1
Natural	9434281704071615	4/7/2017	1	2.27	106	2.610	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.52	108	2.610	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
H&H Sand and Gravel (Guymon, OK)	m001437001	Texas Co.	7001

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434942107291200	7/29/2021	1	3.32	110	2.622	1
Natural	9825241907111130	7/11/2019	1	2.89	112	2.618	
Natural	9434241403271150	3/27/2014	1	3.10	108	2.616	1
Number of Tests:				3	3	3	2
Last 3 Tests Avg.:				3.10	110	2.619	
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				3.10	110	2.619	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
H&H Sand and Gravel Cobb Pit (Guymon, OK)	m014117004	Texas Co.	7004

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082305311224	5/31/2023	1	2.80	108	2.593	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.80	108	2.593	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Southwestern State Sand Corp. (Snyder, OK)	m002587101	Tillman Co.	7101

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082009171015	9/17/2020	1	2.56	109	2.604	1
Natural	9440082006161415	6/16/2020	1	2.39	108	2.600	1
Natural	9625741603010820	3/1/2016	IA 1	2.72	105	2.604	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.56	107	2.603	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.56	107	2.603	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Anchor Sand, Delaware Ave. (Jenks, OK)	m001137217	Tulsa Co.	7217

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082302210951	2/21/2023	1	3.20	112	2.612	2
Natural	9840082203300947	3/30/2022	1	3.30	115	2.609	2
Natural	9440082001141055	1/14/2020	1	3.23	107	2.616	1
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				3.24	111	2.612	2
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				3.11	111	2.611	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Anchor Stone (Jenks, OK)	m008967235	Tulsa Co.	7235

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9434241501261640	1/26/2015	1	2.70	109	2.619	2
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.70	109	2.619	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Anchor Stone Volentine (Broken Arrow, OK)	m009997236	Tulsa Co.	7236

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082001141120	1/14/2020	1	2.88	107	2.608	1
Natural	9434241501261445	1/26/2015	1	2.60	112	2.605	2
Natural	9434241308081314	8/8/2013	1	2.80	111	2.610	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.76	110	2.608	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.76	110	2.608	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Holliday Sand & Gravel Plant#14 (Broken Arrow, OK)	m001657231	Tulsa Co.	7231

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082001141140	1/14/2020	1	3.00	112	2.613	1
Natural	9434241501261500	1/26/2015	1	2.40	109	2.590	3
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.70	111	2.602	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Anchor Stone Choska Sand (Choska, OK)	m013347311	Wagoner Co.	7311

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082201071136	1/7/2022	1	2.69	111	2.610	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.69	111	2.610	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u> Greenhill Sand (Haskell, OK)	<u>P/S Code</u> m012527310	<u>Geog. Area</u> Wagoner Co.	<u>Pit Num.</u> 7310
--	--------------------------------------	---	--------------------------------

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082103181107	3/18/2021	1	3.11	111	2.597	1
Number of Tests:				1	1	1	1
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				3.11	111	2.597	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Greenhill Sand Easton Pit (Broken Arrow, OK)	m006267312	Wagoner Co.	7312

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9438872304131130	4/13/2023	1	3.39	117	2.598	1
Natural	9440082302211128	2/21/2023	1	3.52	115	2.623	1
Natural	9840082203301223	3/30/2022	1	3.08	110	2.616	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				3.33	114	2.612	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				3.33	114	2.612	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Holliday Sand & Gravel Plant#10 (Coweta, OK)	m002007301	Wagoner Co.	7301

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082302211201	2/21/2023	1	2.93	110	2.572	2
Natural	9440082103181146	3/18/2021	1	2.96	110	2.613	2
Natural	9440082004301145	4/30/2020	1	2.89	110	2.615	2
Number of Tests:				4	4	4	4
Last 3 Tests Avg.:				2.93	110	2.600	2
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.86	110	2.599	2

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Holliday Sand & Gravel Plant#17 (Broken Arrow, OK)	m002097308	Wagoner Co.	7308

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082302211027	2/21/2023	1	2.97	112	2.613	1
Natural	9440082004301230	4/30/2020	1	2.83	111	2.600	2
Natural	9434241409241356	9/24/2014	1	2.50	109	2.614	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.77	111	2.609	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.77	111	2.609	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

<u>Producer/Supplier Name</u>	<u>P/S Code</u>	<u>Geog. Area</u>	<u>Pit Num.</u>
Holliday Sand & Gravel Plant#20 (Haskell, OK)	m006497304	Wagoner Co.	7304

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082004301115	4/30/2020	1	2.63	110	2.618	2
Natural	9800721809131100	9/13/2018	1	2.55	110	2.608	1
Natural	9434241409241325	9/24/2014	1	2.00	109	2.635	1
Number of Tests:				3	3	3	3
Last 3 Tests Avg.:				2.39	110	2.620	1
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.39	110	2.620	1

(QM) HC Conc Aggregate, Fine

Test Data Report

Description of Test Result Indicators	
Ind.	Description
A	Finess Modulus
B	Unit Weight (lb/cu. ft.) T19
C	Specific Gravity T84
D	Colormetric T21

Producer/Supplier Name	P/S Code	Geog. Area	Pit Num.
Kline Materials Woodward Sand Plant (Woodward, OK m002207701		Woodward Co.	7701

Aggr. Type	Smpl. ID	Smpl. Date	Smpl. Tst. Nbr.	A	B	C	D
Natural	9440082106151203	6/15/2021	1	2.58	106	2.645	1
Natural	9434281511020800	11/2/2015	1	2.71	110	2.620	1
Number of Tests:				2	2	2	2
Last 3 Tests Avg.:							
Last 5 Tests Avg.:							
Last 10 Tests Avg.:							
Total Avg.:				2.65	108	2.633	1