

Report Date: 01/01/03

**Average Specific Gravities 60/60°F,  
Pounds/Gallon at 60°F and Percent Residual,  
for Approved Cutbacks per Materials Division Policy for Acceptance**

<b>Refinery</b>	<b>Units</b>	<b>MC-30</b>	<b>MC-70</b>	<b>MC-250</b>	<b>MC-800</b>	<b>MC-3000</b>
Frontier Muskogee, Oklahoma	Spec. Grav.	.9230				
	Lbs/Gal.	7.6862				
	% Residual	59.0				
Wynnewood Refinery (Gary Williams Energy) Wynnewood, Oklahoma	Spec. Grav.	0.9173	0.9385	0.9572	0.9718	0.9852
	Lbs/Gal.	7.6386	7.8158	7.9715	8.0934	8.2046
	% Residual	58.5	65.6	75.3	82.6	89.0

Average Specific Gravity to be used on all ODOT projects  
from January 1, 2003, thru December 31, 2003.

Marcella Donovan  
Liquid Asphalt

Reynolds Toney, P.E.  
Materials Engineer