

REPORT DATE: 1/7/04

**Average Specific Gravities 60/60°F,  
Pounds/Gallon at 60°F and Percent Residual,  
for Approved Cutbacks per Materials Division Policy for Acceptance**

<b>Refinery</b>	<b>Units</b>	<b>MC-30</b>	<b>MC-70</b>	<b>MC-250</b>	<b>MC-800</b>	<b>MC-3000</b>
Gary Williams Energy Corp. Wynnewood, Oklahoma	Spec. Grav.	0.9223	0.9407	0.9555	0.9699	0.9845
	Lbs/Gal.	7.6804	7.8338	7.9572	8.0773	8.1991
	% Residual	58.5	67.2	75.6	82.5	89.2
Trigeant EP, Ltd. El Dorado, Kansas	Spec. Grav.	0.9427			1.0064	
	Lbs/Gal.	7.8510			8.3816	
	% Residual	58.5			82.9	
Valero McKee (Sunray), Texas	Spec. Grav.	0.9279	0.9462			
	Lbs/Gal.	7.7271	7.8780			
	% Residual	56.3	67.0			

Average Specific Gravity to be used on all ODOT projects  
from January 1, 2004, thru December 31, 2004.

Marcella Donovan  
Liquid Asphalt

Reynolds Toney, P.E.  
Materials Engineer