

REPORT DATE: 4/23/04

**Average Specific Gravities 60/60°F,
Pounds/Gallon at 60°F and Percent Residual,
for Approved Cutbacks per Materials Division Policy for Acceptance**

Refinery	Units	MC-30	MC-70	MC-250	MC-800	MC-3000
Frontier Terminal & Trading Muskogee, Oklahoma	Spec. Grav. Lbs/Gal. % Residual		0.9494 7.9063 66.8			
Gary Williams Energy Corp. Wynnewood, Oklahoma	Spec. Grav. Lbs/Gal. % Residual	0.9223 7.6804 58.5	0.9407 7.8338 67.2	0.9555 7.9572 75.6	0.9699 8.0773 82.5	0.9845 8.1991 89.2
Trigeant EP, Ltd. El Dorado, Kansas	Spec. Grav. Lbs/Gal. % Residual	0.9427 7.8510 58.5			1.0064 8.3816 82.9	
Valero McKee (Sunray), Texas	Spec. Grav. Lbs/Gal. % Residual	0.9279 7.7271 56.3	0.9462 7.8780 67.0			

Average Specific Gravity to be used on all ODOT projects
from January 1, 2004, thru December 31, 2004.

Marcella Donovan
Liquid Asphalt

* Revised April 23, 2004 - Added Frontier Terminal & Trading MC-70

Reynolds Toney, P.E.
Materials Engineer