

REPORT DATE: 6/14/04

**Average Specific Gravities 60/60°F,  
Pounds/Gallon at 60°F and Percent Residual,  
for Approved Cutbacks per Materials Division Policy for Acceptance**

<b>Refinery</b>	<b>Units</b>	<b>MC-30</b>	<b>MC-70</b>	<b>MC-250</b>	<b>MC-800</b>	<b>MC-3000</b>
Frontier Terminal & Trading Muskogee, Oklahoma	Spec. Grav. Lbs/Gal. % Residual		0.9494 7.9063 66.8			
Gary Williams Energy Corp. Wynnewood, Oklahoma	Spec. Grav. Lbs/Gal. % Residual	0.9223 7.6804 58.5	0.9407 7.8338 67.2	0.9555 7.9572 75.6	0.9699 8.0773 82.5	0.9845 8.1991 89.2
Koch Pavement Solutions Koch, Muskogee	Spec. Grav. Lbs/Gal. % Residual	0.9356 7.7913 58.6	0.9532 7.9381 65.5			
Trigeant EP, Ltd. El Dorado, Kansas	Spec. Grav. Lbs/Gal. % Residual	0.9427 7.8510 58.5			1.0064 8.3816 82.9	
Valero McKee (Sunray), Texas	Spec. Grav. Lbs/Gal. % Residual	0.9279 7.7271 56.3	0.9462 7.8780 67.0			

Average Specific Gravity to be used on all ODOT projects  
from January 1, 2004, thru December 31, 2004.

Marcella Donovan  
Liquid Asphalt

\* Revised April 2004 - Added Frontier Terminal & Trading MC-70

\*\* Revised June 2004-Added Koch Pavement Solutions

Reynolds Toney, P.E.  
Materials Engineer