

REPORT DATE: 1/13/05

**Average Specific Gravities 60/60°F,
Pounds/Gallon at 60°F and Percent Residual,
for Approved Cutbacks per Materials Division Policy for Acceptance**

Refinery	Units	MC-30	MC-70	MC-250	MC-800	MC-3000
Frontier Terminal & Trading Catoosa, Oklahoma	Spec. Grav. Lbs/Gal. % Residual	0.9313 7.7554 57.5				
Frontier Terminal & Trading Muskogee, Oklahoma	Spec. Grav. Lbs/Gal. % Residual	0.9343 7.7804 59.5	0.9494 7.9063 66.8		0.9916 8.2582 83.5	1.0143 8.4475 90.5
Gary Williams Energy Corp. Wynnewood, Oklahoma	Spec. Grav. Lbs/Gal. % Residual	0.9267 7.7172 58.7	0.9407 7.8338 66.9	0.9598 7.9930 76.2	0.9664 8.0398 83.3	0.9887 8.2340 89.5
Koch Pavement Solutions Koch, Muskogee	Spec. Grav. Lbs/Gal. % Residual	0.9346 7.7892 57.7	0.9532 7.9381 65.5	0.9752 8.1215 75.5	0.9913 8.2557 81.5	1.0064 8.3186 90.5
Trigeant EP, Ltd. El Dorado, Kansas	Spec. Grav. Lbs/Gal. % Residual	0.9427 7.8510 58.5			1.0064 8.3816 82.9	
Valero McKee (Sunray), Texas	Spec. Grav. Lbs/Gal. % Residual	0.9340 7.7779 56.0	0.9462 7.8780 67.0		0.9826 8.1832 84.5	

Average Specific Gravity to be used on all ODOT projects
from January 1, 2005, thru December 31, 2005.

Marcella Donovan
Liquid Asphalt
Reynolds Toney, P.E.
Materials Engineer