

REPORT 1/05/2006

**Average Specific Gravities 60/60°F
and Pounds/Gallon at 60°F
for Approved Asphalt Cements per Materials Division Policy for Acceptance**

Refinery	P/S #	Units	PG 64-22 0K	PG 70-28 0K	AC20-5TR	PG 76-28 0K
Frontier CIC Muskogee, Oklahoma	m00510	Spec. Grav. Lbs/Gal.	1.0321 8.5959	1.0257 8.5426		1.0285 8.5659
Sem Materials Muskogee, Oklahoma	m00314	Spec. Grav. Lbs/Gal.	1.0353 8.6226			
Gary Williams Energy Corp. Wynnewood, Oklahoma	m00357	Spec. Grav. Lbs/Gal.	1.0174 8.4734	0.9990 8.3199		
Sem Materials Muskogee ,Oklahoma	m00511	Spec. Grav. Lbs/Gal.	1.0354 8.6235	1.0274 8.5567		1.0288 8.5684
SemMaterials Catoosa,Oklahoma	m00618	Spec. Grav. Lbs/Gal	1.0340 8.6618			
Sem Materials Saginaw, Texas	m00547	Spec. Grav. Lbs/Gal.	1.0348 8.6184	1.0284 8.5651		1.0251 8.5375
Valero Catoosa ,Oklahoma	m00347	Spec. Grav. Lbs/Gal.	1.0260 8.5451	1.0218 8.5100		1.0232 8.5219
Sinclair Tulsa, Oklahoma	m00348	Spec. Grav. Lbs/Gal.	1.0311 8.5876			
Valero Ardmore, Oklahoma	m00352	Spec. Grav. Lbs/Gal.	1.0244 8.5317	1.0178 8.4759		1.0183 8.4809
Valero Ark City, Ks	m00512	Spec. Grav. Lbs/Gal.	1.0295 8.5743			
Valero McKee , Texas	m00311	Spec. Grav. Lbs/Gal.	1.0142 8.4467			
Wright Asphalt Catoosa, Oklahoma	m00635	Spec. Grav. Lbs/Gal			1.0279 8.5609	
Trumbull Oklahoma City, Oklahoma	m00354	Spec. Grav. Lbs/Gal.	1.0159 8.4609			

Average Specific Gravity to be used on all ODOT projects
from January 1, 2006, thru December 31, 2006

Marcella Donovan
Reynolds Toney, P.E

Liquid Asphalt
Materials Engineer